

ClassicVue™ Solid Liner Data Sheet

As at 30 May 2023

Product Codes: CFEABWSL

Applications	Exterior mount to mass transit vehicles requiring premium quality grade type film. High tolerance in challenging installation and in-use conditions. This is an APNO specified film and is approved for use on buses.
Makeup	Calendered polymeric flexible perforated black (adhesive side) / white (printable side) gloss PVC with clear pressure-sensitive adhesive and single layer solid unperforated paper liner.
Vinyl Thickness	203 microns, approx.
Release Liner	Solid paper liner, 178 microns, approx.
Adhesive	25 microns, approx. Removable acrylic adhesive
Perforation Size and Pattern	1.5mm, 50% / 50% open/closed areas
Standard Width/Length	Boxed 1370mm x 60m on 76mm core.
Dimensional Stability	Good
Application Temperatures	Recommended: 15°C to 25°C, Min: 4°C Max: 30°C (in shade)
Service Temperature Range	-17°C to +60°C
Durability	At least 5 years. 6 months for clean removal. Adhesion may increase with time.
Water & Humidity Resistance	Fair, immersion in water not recommended.
Solvent Resistance	Good
Storage Stability	12 months shelf life when stored at 21°C & 50% relative humidity
Printing	Compatible with solvent (including mild and eco), screen and latex. Not compatible with UV-cure inks. Print image on white (non-adhesive) side. Testing recommended before production to determine appropriate profile settings.
Out Gassing	1 - 3 days when suspended vertically in ventilated area. Trim after out gas period.
Matching Overlaminates	CurvaLam or AutoLam only. Do not use any other film. Refer to our Laminating One Way Vision Information Sheet. Cold press only using a laminating machine. After laminating, wait 24 hours before applying to window.
Installation	Refer to the Surface Preparation and Installation Instruction Fact Sheets. Apply to clean, dry, tepid temperature glass surface. Use mild liquid soap (wax free) and water, dry glass well with clean lint free cloth and 100% IPA. Do NOT use ammonia, Windex®, vinegar, methylated spirits, Prep-Wash, Prep-Sol, citrus cleaners or other solvent-based glass cleaner prior to application. Do not use heat.
Removal	Refer to the Care and Removal Fact Sheet. Remove by peeling from surface.
Warranty and Disclaimer	12 months from date of purchase. Refer to the Warranty Statement.

The information in this data sheet is presented for reference and illustration of general product characteristics only. The information does not constitute a representation or warranty relating to the suitability or fitness for a particular application or otherwise create guarantees of product performance. **In all cases, purchasers should independently determine, prior to use, the suitability of this product for their specific application.**